









Glass Enamels






Product Series	Type	Temperature Range	Application	Characteristics
10	High Temperature Glass Color	620-700	Curved Glass Tempered Glass	Chemical resistant
11	Low Temperature Glass Color	540-580	Cosmetic Bottle Glass Lamp	Non-chemical resistant
12R	Medium-High Temperature Glass Color	600-630	Beverage bottle	Chemical Resistant

10 Series Glass Enamels for 620-700° C - Curved Glass, Tempered Glass
















Product	Color	
10101	Light Green	
10161	Green	
10201	Peacock Blue	
10202	Peacock Green	
10294	Blue	
10306	Yellow	
10308	Orange	
10725	Red	
10705	Dark Red	
10603	Light Brown	
10608	Brown	
10905	White (Opaque)	
10911	Satin White (Semitransparent)	
10772	Purple	
10448	Black	

11 Series Glass Enamels for 540-580° C - Cosmetic Bottles, Glass Lamps

Product	Colour	
11101	Light Green	
11161	Green	
11201	Peacock Blue	
11202	Peacock Green	
11294	Blue	
11306	Yellow	
11308	Orange	

11725	Red	
11705	Dark Red	
11603	Light Brown	
11608	Brown	
11905	White (Opaque)	
11911	Satin White (Semitransparent)	
11772	Purple	
11448	Black	

12R Series Glass Enamels for 600-630° C - Beverage bottles

Product	Color	
12101R	Light Green	
12161R	Green	
12201R	Peacock Blue	
12202R	Peacock Green	
12294R	Blue	
12306R	Yellow	
12308R	Orange	
12725R	Red	
12705R	Dark Red	
12603R	Light Brown	
12608R	Brown	
12906R	White (Opaque)	
12911R	Satin White (Semitransparent)	
12772R	Purple	
12448R	Black	

Presentation: Product can be supplied in

- (1) powder form
- (2) oil-based screen printing medium
- (3) thermoplastic screen printing medium

Miscibility:

Products in the series can be mixed to yield the desired color.

Application Guide:

Decal printing Use 150-250 mesh screen, 10:6 powder to medium ratio
Direct screen printing Use 150-250 mesh screen, 10:6 powder to medium ratio